

IN THE CLAIMS

Please amend the claims as follows:

1. (Original) A thermoplastic resin composition comprising:  
a polylactic acid polymer (A);  
an acrylic polymer (B) containing a methyl methacrylate monomer unit; and  
a graft copolymer (C) obtained by graft-polymerizing a vinyl monomer onto a  
rubbery polymer,  
wherein the refractive index,  $R_c$ , of the graft copolymer (C) and the total refractive  
index,  $R_{ab}$ , of the polylactic acid polymer (A) and the acrylic polymer (B) satisfy the  
following formula (1).  
$$-0.004 \leq R_c - R_{ab} \leq +0.008 \quad (1)$$
2. (Original) The thermoplastic resin composition according to claim 1, wherein the  
compositional ratio of the polylactic acid polymer (A) to the acrylic polymer (B) is within the  
range of from 1 / 99 to 99 / 1 (mass ratio).
3. (Original) The thermoplastic resin composition according to claim 1, wherein 1 to 50  
parts by mass of the graft copolymer (C) to 100 parts by mass of the total of the polylactic  
acid polymer (A) and the acrylic polymer (B) is blended.
4. (Original) The thermoplastic resin composition according to claim 1, wherein the  
graft copolymer (C) is obtained by using a silicone rubber containing a polyorganosiloxane or  
an acrylic rubber containing a polyalkyl (meth)acrylate rubber as the rubbery polymer.

5. (Original) A molded article obtained by molding the thermoplastic resin composition according to claim 1.
6. (Original) The molded article according to claim 5, wherein total light transmittance of the molded article is 65% or more.
7. (Original) The molded article according to claim 6, wherein haze of the molded article is 60% or less.
8. (New) A molded article obtained by molding the thermoplastic resin composition according to claim 2.
9. (New) A molded article obtained by molding the thermoplastic resin composition according to claim 3.
10. (New) A molded article obtained by molding the thermoplastic resin composition according to claim 4.